

TECHNICAL DATA SHEET NO: P16 VERSION: 2-17/11/14 PAGE: 1 OF 2 DATE OF ISSUE: 7/3/2015

# **EVERBUILD P16 PLUMBERS PVC PIPE CEMENT**



Colour	<b>Product Code</b>	Pack Size	<b>Box Qty</b>
-	P16PIPE	250ML	12

#### **Product Description**

P16 PVC PIPE CEMENT is a non-drip, thixotropic solvent based plastic pipe cement for use with pressure and non-pressure applications. P16 PVC PIPE CEMENT with a rapid rate of bond strength development

## **Benefits**

- Rapid bond strength development.
- Easy to apply thixotropic paste.
- Kite marked to BSEN 14680.
- CE compliant to 14814

## **Areas for Use**

- Bonding uPVC Pipes and accessories in pressure systems up to 16PN according to BSEN 14814, specifically for bonding thermoplastic piping systems that conform to BSEN 1329.
- Bonding Pipes and accessories in waste systems according to the following standards:
  - PVC-U plastic piping systems for soil and waste discharge (low and high temperature) BSEN 1329.
  - ABS piping systems for soil and waste discharge (Low and high temperature)
    BSEN 1455.
  - PVC -C plastic piping systems for soil and waste drainage (low and high temperature) BSEN 1566.

## Limitations

- Do not use in conjunction with potable water.
- Do not dip pipes into adhesive.
- Reseal immediately after use.

## **Application**

Wear suitable protective clothing and gloves before use. Avoid inhalation of vapours' and extinguish all sources of ignition.

All surfaces to be joined must be clean sound and dry. Cut pipes squarely. Remove any swarf and chamfer the outside edge. Lightly abrade pipe with emery cloth and degrease with a proprietary solvent such as Stick 2 Contact Adhesive Thinner and Cleaner. Check the two ends fit together correctly.

Apply a thin and even layer of adhesive to both surfaces with a brush. Slide the pipes together immediately. DO NOT TWIST. Hold in place for 20-30 seconds and remove excess adhesive with a



VERSION: 2-17/11/14

TECHNICAL DATA SHEET NO: P16

PAGE: 2 OF 2 DATE OF ISSUE: 7/3/2015

cloth. Allow at least 10 minutes drying time before handling and at least 8 hours before putting into service (non-pressure) or 24 hours (pressure applications).

## **Health & Safety**

Consult MSDS for full list of hazards.

#### Coverage

Approx.  $0.6m^2$  per 250ml can when applied as directed enough for 31 x 32mm diameter joints or 6 x 90mm joints.

## **Storage**

Store in original container away from frost in a dry area.

## **Shelf Life**

12 months in original unopened containers when stored between +5°C and +35°C

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.