

# PRODUCT DATA SHEET

## Sika® Mix PMP

### PRE-MEASURED AIR ENTRAINING ADMIXTURE

#### PRODUCT DESCRIPTION

Sika® Mix PMP is a mortar plasticiser in powder form for use as an alternative to lime or as a supplement to lime to aid mortar durability. Sika® Mix PMP will entrain microscopic air bubbles into cement mortars in a controlled manner as specified in EN934. Air entrained mixes produce greatly enhanced working properties with a reduced demand for mixing water. Sika® Mix PMP also improves frost resistance in both freshly laid and hardened mortars, as the microscopic air bubbles entrained provide space for expansion of water due to freezing.

#### USES

- For use as an admixture for mortars to improve workability in bricklaying, pointing bricks and rendering mortars.
- Can be used in cement, sand and cement, lime, and sand mortars.

#### CHARACTERISTICS / ADVANTAGES

- Economical: - reduced labour costs - reduced wastage - increased spread rates
- Helps reduce efflorescence
- Reduces bleed and segregation in the mix
- Improves frost resistance
- Can be used down to -2°C
- Ready to use sachets

#### PRODUCT INFORMATION

<b>Packaging</b>	250 Sachets, in a plastic tub
<b>Appearance / Colour</b>	Straw/Yellow
<b>Shelf Life</b>	Two years when stored in accordance with the manufacturer's instructions.
<b>Storage Conditions</b>	Store in cool (5 – 25°C), dry conditions.
<b>Total Chloride Ion Content</b>	<0.1% (w/w)

Cement:Sand + Sika® Mix PMP	Cement:Lime Sand	Typical Uses
1:3	1:¼:3	Laying load-bearing brick work.
1:4	1:½:4.5	External rendering (exposed positions). Backing and bedding coats (rough cast).
1:6	1:1:6	Internal plaster Floating coats External rendering.
1:3 to 1:6	Varies	Brickwork, pointing or re-pointing.
1:8	1:2:9	Laying blocks and concrete or sand-lime bricks.

#### APPROVALS / STANDARDS

- Complies with EN934-3

## APPLICATION INFORMATION

### Recommended Dosage

Sika® Mix PMP is added at the rate of 1 sachet per 25Kg bag of cement. Always use the type of sand recommended for a particular application. Test mixes should be carried out to determine optimum dosage

## APPLICATION INSTRUCTIONS

Sika® Mix PMP may be added directly into the mixing drum after the addition of sand or pre-mixed with the gauging water. The use of Sika® Mix PMP pre-weighed sachets introduced directly to the mix optimises control of dosage and minimises wastage.

The action of Sika® Mix PMP is entirely physical and therefore requires an efficient mixing action. If mixing is to take place by hand the mix must be well “turned over” to achieve the maximum plasticising effect. Mortar selection should be made in line with the relevant National Standards and Codes of Practice. The table above gives indicative mix designs relative to uses with and without Sika® Mix PMP. Portland Cement: Lime, sand mixes which also include an air entraining plasticiser have been shown to be particularly durable in accelerated testing.

## VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### EVERBUILD BUILDING PRODUCTS LTD

Site 41, Knowsthorpe Way  
Cross Green Industrial Estate  
Leeds, LS9 0SW  
Tel: 0113 240 3456  
Web: [www.everbuild.co.uk](http://www.everbuild.co.uk)  
Twitter: @everbuild

### SIKA LIMITED

Watchmead  
Welwyn Garden City  
Hertfordshire, AL7 1BQ  
Tel: 01707 394444  
Web: [www.sika.co.uk](http://www.sika.co.uk)  
Twitter: @SikaLimited

### SIKA IRELAND LIMITED

Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland

SikaMixPMP-en-GBEVER-(03-2018)-1-1.pdf